



Where innovative ideas take hold.

TECHNICAL BULLETIN

HANDLING AND STORAGE OF METAL BUILDING FACINGS

PRE-LAMINATION:

There are no special requirements for handling and storage of Compac metal building facings prior to lamination to fiberglass, beyond normal good practices.

DURING LAMINATION:

Avoid running facing over sharp edges or dirty rollers. Avoid insufficient, or excess, application of laminating adhesive.

POST- LAMINATION:

Place laminated insulation in perforated bags only. Bags must be able to breathe. Do not store bags on freshly poured concrete.

Bags should not be stored directly on ground.

Do not store bags where they are subject to rainfall exposure.

Exercise care to avoid dragging facing over sharp structural components.

If bluish-brown discoloration is observed on FSK (Foil-Scrim-Kraft) facing, this is oxidation of the foil which will not affect the product functionally.

FURTHER INFORMATION:

For further information or with specific questions, please call our technical service manager at 1-877-5COMPAC (1-877-526-6722).

Cp10-25-05